



Kromatis® Indoor

Clear Binder

PROPERTIES		TEST METHOD	Kromatis® Indoor
Penetration at 25 °C	(^{1/10} mm)	EN 1426	< 10
Softening Point (Ring & Ball)	(°C)	EN 1427	≥ 80
Density at 25 °C		EN ISO 3838	1.002 *
Flash Point (Cleveland)	°C	EN ISO 2592	≥ 240
Fraass Breaking Point	°C	EN 12593	- 5
Dynamic Viscosity at 160°C	Pa.s	EN 13702	0.200 *
Color ASTM		ASTM D H4	≤ 7
Elastic recovery at 25°C	%	EN 13398	70
Compaction temperature	°C		160 - 170

*Typical value

Packaging

	Bulk	Thermo-melt bags 500g	Drums of 190 kg
Kromatis® Indoor		●	

Kromatis® is a registered brand of TotalEnergies.

Safety Data Sheet are available on Internet : <https://ms-sds.totalenergies.com/>

Version: 2022-08

The technical information on this sheet is provided for information only and is not exhaustive. These data cannot in any case engage our responsibility for the processes of use of the product and the result obtained. The choice and development of these processes is the responsibility of users in their entire responsibility. For more information, contact our sales department.