



Altek®

160 RA NF5

Bitume compatible avec les polymères SBS

CARACTERISTIQUES	METHODE	SPECIFICATIONS	
Pénétrabilité à 25°C	^{1/10} mm	EN 1426	140 – 180
Point de ramollissement Bille et anneau	°C	EN 1427	37 – 45
Densité relative à 25°C	-	EN ISO 3838	1,00 – 1,07
Point éclair Cleveland	°C	EN ISO 2592	≥ 230
Solubilité	%	EN 12592	≥ 99,0
Teneur en paraffines	%	EN 12606-2	≤ 4,5

Le bitume **Altek® 160 RA NF5** est adapté aux mélanges avec des polymères de type SBS (styrène-butadiène-styrène) pour la fabrication de feuilles d'étanchéité.

Altek® est une marque enregistrée de TotalEnergies.

Les fiches de données de sécurité sont disponibles sur Internet :

<https://ms-sds.totalenergies.com>

Version: 2023-03

The technical information on this sheet is provided for information only and is not exhaustive. These data cannot in any case engage our responsibility for the processes of use of the product and the result obtained. The choice and development of these processes is the responsibility of users in their entire responsibility. For more information, contact our sales department.