

SCRIPTANE PW

DEAROMATIZED SOLVENTS FOR PRINTING INKS

Typical values 

PROPERTIES	UNITS	METHODS	SCRIPTANE PW 24/27 H	SCRIPTANE PW 25/28 H	SCRIPTANE PW 25/33 H	SCRIPTANE PW 28/32 H	SCRIPTANE PW 30/35 H
DENSITY AT 15°C (59°F)	kg/m ³	ASTM D4052	817	818	815	815	816
SAYBOLT COLOR	Unit Saybolt color	ASTM D6045	+30	+30	+30	+30	+30
BOILING RANGE: INITIAL POINT	°C (°F)	ASTM D86	240 (464)	250 (482)	254 (489)	278 (532)	303 (577)
FINAL POINT			262 (504)	277 (531)	326 (619)	318 (604)	346 (655)
FLASH POINT	°C (°F)	ASTM D93	104 (220)	116 (241)	120 (248)	137 (279)	160 (320)
AROMATIC CONTENT	mg/kg (ppm)	UV Internal method	< 30	< 30	< 60	< 80	< 150
BENZENE CONTENT	mg/kg (ppm)	ASTM D6229	< 1	< 1	< 1	< 1	< 1
SULPHUR CONTENT	mg/kg (ppm)	ASTM D5453	< 1	< 1	< 1	< 1	< 1
ANILINE POINT	°C (°F)	ASTM D611	79 (174)	84 (183)	89 (192)	92 (198)	100 (212)
KAURI BUTANOL	KB Unit	ASTM D1133	26	25	23	22	20
VISCOSITY AT 40°C (104°F)	mm ² /s	ASTM D445	2.4	2.9	3.6	4.2	6.0

CARBON CHAIN LENGTH HSPA	C13 - C18	C14 - C18	C14 - C18	C16 - C20	C13 - C23
CAS NUMBER	64742-46-7 (R)	64742-46-7 (R)	64742-46-7 (R)	64742-46-7 (R)	64742-46-7 (R)
EC NUMBER	928-253-0	927-632-8	927-632-8	919-029-3	932-078-5

Data provided in this table is issued in good faith to the best of our knowledge, but no warranty, expressed or implied is given.
R: Related CAS number.